

BAR SIZE	* LOCATION CATEGORY		
	A	B	C
#4	2'-5"	1'-9"	1'-5"
#5	3'-0"	2'-2"	1'-9"
#6	3'-7"	2'-7"	2'-1"
#7	4'-10"	3'-6"	2'-10"
#8	6'-5"	4'-7"	3'-8"
#9	8'-1"	5'-9"	4'-8"
#10	10'-3"	7'-4"	5'-11"
#11	12'-7"	9'-0"	7'-3"

* LOCATION CATEGORY

- A - Bars in horizontal layers in top of pour with 12" or more of concrete below them such as in: footings, pier caps, etc.
 B - All bars not in Category A spaced less than 6" apart.
 C - All bars not in Category A spaced 6" or more apart.

Note:

- When bar lap is not specified on the Plans, the above dimensions shall be used.
- These bar laps do not apply when bar is in lightweight concrete. Greater lengths are required for this material.
- These bar laps only apply where the General Notes indicate "Reinforcing Steel Design, $f_y = 60$ ksi."

APPROVAL	
<i>L. S. Fisher</i> DIRECTOR	
OFFICE OF STRUCTURES	
DATE: 4/30/81	
REVISIONS	
SHA	FHWA
11-23-93	.
1-22-01	.
9-20-05	.
11-26-07	.

FHWA APPROVAL
DATE: 7-19-11

STATE OF MARYLAND
DEPARTMENT OF TRANSPORTATION
STATE HIGHWAY ADMINISTRATION
OFFICE OF STRUCTURES

BAR LAP DIMENSIONS FOR
GRADE 60 REINFORCING STEEL
IN MIX NO.3 (3500 P.S.I.) CONCRETE
NON-EPOXY COATED REINFORCING

STANDARD NO. M(6.07)-81-127(L)

SHEET 1 OF 3



MISCELLANEOUS